

**SPECIFICATION****For****8.7/15KV-CVT**

8.7/15(17.5)kV

XLPE Insulated PVC Sheathed

Triplex Type Power Cable

(8.7/15(17.5)kV, Cu/XLPE/CTS/PVC)

BY Wade  
(Wachara Sangsomritphon)

MANAGER, Cable Design Section

APP. Surachart Mame  
(Surachart Mame)

MANAGER, Development Department

APP. \_\_\_\_\_  
( )

CUSTOMER

Rev.	Date	Description
0	4/4/2024	Issued specification

Customer Document	Rev.

**Remark:**

This document is based on the Customer Document for the structure and properties of electric wire and cable only. If there are different points, will be shown in deviation table.

## **1. Scope**

This specification covers 16500V copper conductor cross-linked polyethylene (XLPE) insulated polyvinyl chloride (PVC) sheathed triplex type power cable.

The cable shall be in accordance with IEC 60502-2 : 2014.

The finished cables shall meet the flame test requirements per IEC 60332-1.

## **2. Conductor**

The conductor shall be compacted concentric stranded uncoated annealed copper conductor in accordance with IEC 60228 : 2004, Class 2.

The direction of lay shall be left-hand (S) lay in the outermost layer.

## **3. Conductor Shield**

The conductor shield shall be a semi-conducting nylon tape and shall be applied helically with a wrap over the conductor and a layer of extruded semi-conducting compound.

Size  $\leq 150 \text{ mm}^2$  : Applied extruded semi-conducting compound

Size  $\geq 185 \text{ mm}^2$  : Applied semi-conducting nylon tape and extruded semi-conducting compound

The thickness of the conductor shield shall be approximate 0.5 mm.

## **4. Insulation**

The insulation shall be cross-linked polyethylene (XLPE) compound meet the requirements of IEC 60502-2 : 2014.

The average thickness of the insulation shall be not less than that given in Table 1.

The minimum thickness shall not fall below 90% of the nominal value in Table 1 by more than 0.1 mm.

## **5. Insulation Shield**

The insulation shield shall be a layer of extruded semi-conducting compound and shall be free stripping.

The thickness of the insulation shield shall be approximate 0.5 mm.

## **6. Metallic Shield**

The metallic shield shall be an uncoated annealed copper tape and shall be applied helically with a lap over the insulation shield.

The thickness of the copper tape shall be approximate 0.1 mm.

A suitable separator tape shall be applied helically over the shielded core.

## **7. Core Identification**

The cores shall be identified by colors of identification tape, placed longitudinally applied over the insulation shield, as follow :

3-cores : white, red, blue

## **8. Sheath**

The sheath shall be sunlight resistant polyvinyl chloride (PVC/ST2) compound meet the requirements of IEC 60502-2 : 2014.


The average thickness of the sheath shall be not less than that given in Table 1.

The minimum thickness shall not fall below 80% of the nominal value in Table 1 by more than 0.2 mm.

The color of the sheath shall be black.

## **9. Marking on Cable**

The marking items shall be marked with suitable means throughout the length of cable.

1. Manufacturer's name and/or trade mark "  YAZAKI.....TYE"
2. Year of manufacture
3. Rated circuit voltage "8.7/15(17.5)KV"
4. Type of insulation "XLPE"
5. Type of cable "POWER CABLE"
6. Number of cores and size of conductor

## **10. Triplexing**

The individual sheathed core shall be cables together.

The direction of lay shall be left-hand (S) lay.

The length of lay shall be 25 to 60 times the diameter of one of the sheathed.

## **11. Test and Properties**

The cable shall meet the requirements in Test and Inspection and Table 1 , when tested in accordance with IEC 60502-2 : 2014, IEC 60228 : 2004 and IEC 60332-1.


Remark: Sunlight resistant test meet the requirement of TIS 293-2541.

**12. Packing**

The cable shall be placed on non-returnable wooden reels.

The reels shall be covered with suitable covering to provide the cable with physical protection during transportation and during ordinary storage and handling operations.

Each reel shall be clearly marked as follows.

1. Designation "8.7/15KV-CVT"
2. Number of cores and size of conductor
3. Cable length
4. Net and gross weight
5. Manufacturer's name and/or trade mark "  **YAZAKI** "
6. Rolling direction of reel

## Test and Inspection

### Routine Tests

- Maximum conductor resistance, Ohm/km.....specified in Table 1
- AC test voltage for 5 minutes, kV.....30.5
- Maximum partial discharge level\*.....10 pC or better, at 15.05 kV
- Electrical test on over sheath .....No breakdown

\*The partial discharge level shall be no detectable discharge exceeding the declared sensitivity

### Sample Tests

- Construction.....specified in Table 1
- AC test voltage for 4 hours, kV.....35
- Hot set test at  $200\text{ }^{\circ}\text{C} \pm 3\text{ }^{\circ}\text{C}$  for XLPE
  - Maximum elongation under load (%) .....175
  - Maximum permanent elongation after cooling (%).....15

### Type Tests

- Flame retardant tested according to IEC 60332-1

### Definition concerning the tests


**Routine tests:** Tests made by the manufacturer on each manufactured length of cable to check that each length meets the specified requirements.

**Sample tests:** Tests made by the manufacturer on samples of completed cable or components taken from a completed cable, at a specified frequency, so as to verify that the finished product meets the specified requirements.

**Type tests:** Tests made before supplying, on a general commercial basis, a type of cable covered by this standard, in order to demonstrate satisfactory performance characteristics to meet the intended application.

### Cable structure

Cross-sectional (Not scale)



No.	Structure	Material
1	Conductor	Stranded annealed copper
2	Nylon tape	Semi-conducting nylon tape (For size $\geq 185 \text{ mm}^2$ only)
3	Conductor shield	Semi-conducting compound
4	Insulation	Cross-linked polyethylene (XLPE)
5	Insulation shield	Semi-conducting compound
6	Metallic shield	Copper tape
7	Separator tape or Binder tape	Spun bond tape or suitable tape
8	Sheath	Polyvinyl chloride (PVC/ST2)

**Application:** Use for installation exposed, or in raceway, wet or dry location, or direct burial in ground.

Maximum conductor temperature of  $90^\circ\text{C}$  for normal operation and  $250^\circ\text{C}$  for short circuit conditions

**Table 1**

No. of cores	Size  (mm <sup>2</sup> )	Conductor  (wires/type)	Conductor diameter approx.  (mm)	Insulation thickness nominal  (mm)	Sheath thickness nominal  (mm)	Sheath diameter approx.  (mm)	Overall diameter approx.  (mm)	Conductor resistance at 20°C maximum (Ohm/km)	Weight of cable approx. (kg/km)	Standard packing length (m)
3	25	7/Compacted	6.00	4.5	1.6	22.5	49.0	0.727	1920	500
3	35	7/Compacted	7.10	4.5	1.7	24.0	52.0	0.524	2310	500
3	50	19/Compacted	8.30	4.5	1.7	25.0	54.5	0.387	2730	500
3	70	19/Compacted	9.90	4.5	1.8	27.0	58.5	0.268	3460	500
3	95	19/Compacted	11.70	4.5	1.8	28.5	62.5	0.193	4330	500
3	120	37/Compacted	13.20	4.5	1.9	30.5	66.0	0.153	5200	500
3	150	37/Compacted	14.60	4.5	1.9	32.0	69.0	0.124	6070	500
3	185	37/Compacted	16.30	4.5	2.0	34.0	74.0	0.0991	7320	300
3	240	61/Compacted	18.70	4.5	2.1	36.5	80.0	0.0754	9170	300
3	300	61/Compacted	20.90	4.5	2.1	39.0	84.5	0.0601	11040	300
3	400	61/Compacted	23.50	4.5	2.2	41.5	90.5	0.0470	13600	300